



Thread Plates

Specifications:

The high strength-to-weight ratio and raised anti-skid patterns, make Hindalco's flooring sheets ideal for use in a number of flooring allocations, especially for bus, truck and rail coaches, loading bays, kick plates, stair treads and catwalks.

The aluminium flooring sheets and plates are resistant to corrosion and denting and able to withstand severe conditions of abrasion.

Light, rust-free, hygienic and easy-to-clean, Hindalco's sheets and plates are manufactured with state-of-the-art equipment and sophisticated process technology. Stringent quality control measures have made them a standard in the aluminium flooring market.

Dimensions			
Parameter	Range	Standard	Tolerance
11/1/2	MAN	The hills	for 1.00 to 1.63 +/-0.10
	N. Ville		for 1.64 to 2.50 +/-0.12
	$W_{\nu}W_{\nu}$	$V_{\nu}/V_{\nu}/V_{\nu}$	for 2.51 to 4.00 +/-0.13
Thickness (mm)	1.00 — 6.00 mm (Base thickness)	$V_1 \setminus V_1 \setminus V_1$	for 4.01 to 6.00 +/-0.15
11	CYVVX	813	+/-3 for width <=1000
Width (mm)	700 — 1219*	1219	+/-4 for width >1000
	135/334	A Village	+/-3 for width <=1000
Length (mm)	3660 max	2438 <i>,</i> 3660	+/-4 for width 1000 - 2000

	1712 200	+/-5 for width 2000 -3000
	1711-171	+/-7 for width >3000
1111	<=6 when length <=1000	
	<=8 when length 1000 — 2000	
11/ 11/	<=10 when length 2000 — 3000	
Diagonal difference (mm)	<=14 when length > 3000 -	

Offer for thickness and width outside the range may be quoted on specific request

Alloy (AA)	Temper	UTS (mpa)		Bend test:	
		Min	Max	radius of bend (T= material thickness)	
3105	0	95	145	close	
3105	M*				
G57S	M*		$\langle \cdot, \cdot \rangle$		
6061	M*	V: \	17.11		
5005	M*	11/	1.11		
	T4	280	11/1		93
7039	T6	315	-1/	5t	

Chemical compo	sition				
Alloy (%)	3105	G57S	6061	5005	7039
Fe	0.70	0.50 — 0.65	0.70	0.70	0.40
Si	0.60	0.50	0.40 — 0.8	0.30	0.30
Mg	0.20 — 0.80	1.40 — 1.65	0.8 — 1.2	0.50 — 1.10	2.30 — 3.30
Mn	0.30 — 0.80	1.20 — 1.40	0.15	0.20	0.10 — 0.40
Cu	0.30	0.20	0.15 — 0.40	0.20	0.10
Zn	0.25	1:1:1:1	0.25	0.25	3.5 — 4.5
Ti	0.10	0.05	0.15		0.10
Cr	0.10	1-11-1	0.04 — 0.35	0.10	0.15 — 0.25
Each (Others)	0.05	0.05	0.05	0.05	0.05
Total (Others)	0.15	0.20	0.15	0.15	0.15
Al	Remainder	Remainder	Remainder	Remainder	Remainder

There maybe some residual oil or oil stain on the sheet surface, unless specially requested.

Packing

The flooring sheets are packed loose or in poly-laminated gunny with hoop iron strap and clip, with edge guards and placed on a wooden pallet.

Applications:

Flooring for buses, trucks and rail coaches

Floors for loading bays, kick plates, stair treads and catwalks